

Disclaimer: This color chart is for reference only and is not to be used for final color matching. Shades may vary due to the color and resolution of your computer screen and/or your particular color printer output. Airolite is not responsible or liable for color matches made with online color chart.



## Finishes & Colors



**AIROLITE**  
The look that works.™

Architectural and High-Performance Louvers, Grilles, Screens, Sun Controls



# Standard Colors

Disclaimer: This color chart is for reference only and is not to be used for final color matching. Shades may vary due to the color and resolution of your computer screen and/or your particular color printer output. Airolite is not responsible or liable for color matches made with online color chart.

Airolite offers 27 standard colors available in AAMA 2605 compliant coatings (70% Kynar® PVDF/ 100% Fluoropolymer FEVE), AAMA 2604 compliant coatings (50% Kynar®/Acroflur®) or AAMA 2603 compliant coatings (Baked Enamel).


		
Bone White GF102	Ivory 031	Ascot White GF120
		
Dover White AL202	Cambridge White GF110	Herring Bone GF107
		
Sandstone GF112	Pueblo Tan GF116	Rawhide AL215
		
Smoke GF104	Sierra Tan GF118	Lindie Bronze AL218
		
Hampton Brown GF105	Spartan Bronze GF113	Classic Bronze GF108
		
Statuary Bronze AL221	Dove Gray AL213	Stone Gray GF103
		
Charcoal AL214	Flat Black 044	Gloss Black 045
		
Coronado Red GF121	Terra Cotta AL217	Hartford Green AL208
		
Capri Blue GF106	Aegean Blue AL204	Patina Green GF114

The samples incorporated in this presentation are as close to production materials as color reproduction technology allows.  
Color samples of metal coupons are available upon request. Custom color matching is available upon request.  
Consult your Airolite representative for additional cost associated with custom colors.

# Mica Colors


Disclaimer: This color chart is for reference only and is not to be used for final color matching. Shades may vary due to the color and resolution of your computer screen and/or your particular color printer output. Airolite is not responsible or liable for color matches made with online color chart.

Airolite offers six standard mica colors available in AAMA 2605 compliant coatings (70% Kynar® PVDF/ 100% Fluoropolymer FEVE). Mica colors are formulated to reproduce the low-gloss metallic luster of anodized aluminum in a wider range of dynamic colors. These colors offer many performance advantages over conventional anodized finishes including longer warranty duration, superior resistance to salt spray, greater color uniformity and better chemical resistance. Additionally, mica coatings are easier to repair and touch-up than conventional anodized finishes. Organic micas are comprised of natural minerals and crushed pearlescent that are highly resistant to harmful environmental effects.



Clear Anodize Mica

GF209



Bright Silver

AL222



Sterling

GF201




Gun Barrel

AL239



Dark Bronze

AL238



Asti

AL236



## Other Options

### Mill Aluminum

Aluminum in the mill finish state will be commercially smooth and substantially free from blisters, inclusions, voids, slivers and kinks. Slight discontinuity resulting from flow and die lines inherent in the extrusion process will exist. Occasional discontinuities that can be reasonably removed making the surface suitable for finishing operations are acceptable. Although aluminum is naturally resistant to corrosion, its appearance changes as a result of weathering and aging. Aluminum in the mill finish state may also have a non-uniform surface appearance resulting from oil, heat and oxide discoloration inherent in the manufacturing process.

### Prime Coat

Louvers and architectural products shall be cleaned, pre-treated and receive a prime coat finish suitable for field painting. Products must be thoroughly cleaned and prepared prior to field application of epoxy, urethane or other heavy-duty coatings. Airolite does not recommend prime coat or field painting of louvers and architectural products. As such, Airolite does not provide formal field cleaning, preparation or painting instructions or recommendations.

The samples incorporated in this presentation are as close to production materials as color reproduction technology allows. Color samples of metal coupons are available upon request. Custom color matching is available upon request. Consult your Airolite representative for additional cost associated with custom colors.



# Anodize Colors

Disclaimer: This color chart is for reference only and is not to be used for final color matching. Shades may vary due to the color and resolution of your computer screen and/or your particular color printer output. Airolite is not responsible or liable for color matches made with online color chart.

The anodize process creates an extremely hard and durable finish on aluminum surfaces. Airolite offers seven industry standard anodize colors on aluminum louver products that meet the performance requirements of AAMA 611. Some degree of color discontinuity within industry standard anodize color range tolerances can be expected. For better color consistency Airolite recommends AAMA 2605 compliant mica coatings in lieu of anodize.




Clear Anodize 215-R1 or 204-R1



Champagne Anodize




Light Bronze Anodize




Medium Bronze Anodize



Dark Bronze Anodize



Extra Dark Bronze Anodize



Black Anodize

## Aluminum Association Specification

Anodize	AA-M10C21A44	AA-M10C21A41	AA-M10C21A31
Class	I	I	II
Minimum Mil Thickness	0.7	0.7	0.4
Airolite Louver Anodize Finish Options	Champagne; Light, Medium, Dark or Extra Dark Bronze; Black	215-R1 Clear	204-R1 Clear
Description	Two-step anodize process incorporating a colorfast electrolytic process following the initial anodize step	Clear, colorless and hard oxide aluminum finish that resists weathering and chemical attack	Clear, colorless and hard oxide aluminum finish that resists weathering and chemical attack
Warranty	5 Year	5 Year	1 Year



The samples incorporated in this presentation are as close to production materials as color reproduction technology allows. Color samples of metal coupons are available upon request. Custom color matching is available upon request. Consult your Airolite representative for additional cost associated with custom colors.



Use the reference chart below to better understand the performance criteria defined by the American Architectural Manufacturers Association (AAMA). To ensure the highest performance coatings on louver products, Airolite recommends specifying an AAMA 2605 compliant coating.

Paint Performance Specifications			
Coatings	100% Fluoropolymer (FEVE) 2-Coat 70% Kynar® (PVDF) 3-Coat 70% Kynar® (PVDF) 4-Coat 70% Kynar® (PVDF)	Wood Grain	Baked Enamel
Warranty (Aluminum Products Only)	10 Year (20 Year Optional)	5 Year	1 Year
Weathering	AAMA 2605	AAMA 2604	AAMA 2603
South Florida Exposure	10 Year	5 Year	1 Year
Color Retention	Delta E Color Change ≤5 Hunter Units	Delta E Color Change ≤5 Hunter Units	Slight Fade
Gloss Retention	Minimum 50%	Minimum 30%	N/A
Chalk Resistance	⇒8 Rating (6 for Whites)	⇒8 Rating	Slight Chalking
Erosion Resistance	<10% Film Loss	<10% Film Loss	N/A
Chemical Tests			
Muriatic Acid Resistance (15 Minute Spot Test)	No Blistering or Visual Change	No Blistering or Visual Change	No Blistering or Visual Change
Mortar Resistance (24 Hour Pat Test)	No Loss of Film Adhesion or Visual Change	No Loss of Film Adhesion or Visual Change	No Loss of Film Adhesion or Visual Change
Nitric Acid Resistance	Delta E Color Change ≤5 Hunter Units	Delta E Color Change ≤5 Hunter Units	N/A
Detergent Resistance	No Loss of Adhesion, No Blistering, No Significant Visual Change	No Loss of Adhesion, No Blistering, No Significant Visual Change	No Loss of Adhesion, No Blistering, No Significant Visual Change
Window Cleaner Resistance	No Blistering or Noticeable Change and No Removal of Film	No Blistering or Noticeable Change and No Removal of Film	N/A
Corrosion			
Salt Spray Resistance (ASTM B117)	4,000 Hours, ⇒ 7 Scribe, ⇒ 8 Blister	3,000 Hours, ⇒ 7 Scribe, ⇒ 8 Blister	1,500 Hours, ⇒ 7 Scribe, ⇒ 8 Blister
Aggressive Salt Spray Resistance (ASTM G85, Annex A5)	2,000 Hours Aggressive Cyclical Corrosion Testing	N/A	N/A
Humidity Resistance	4,000 Hours at 100°F and 100% Humidity, No Visual Change and Few Blisters Size 8	3,000 Hours at 100°F and 100% Humidity, No Visual Change and Few Blisters Size 8	1,500 Hours at 100°F and 100% Humidity, No Visual Change and Few Blisters Size 8
Hardness & Adhesion			
Dry Film Hardness	F Minimum Hardness. No Film Rupture.	F Minimum Hardness. No Film Rupture.	H Minimum Hardness. No Film Rupture.
Film Adhesion	Accordance with ASTM D3359	Accordance with ASTM D3359	Accordance with ASTM D3359
Impact Resistance	No Removal of Film from Substrate	No Removal of Film from Substrate	No Removal of Film from Substrate
Abrasion Resistance	Co-efficient Value 40 Minimum	Co-efficient Value 20 Minimum	N/A





The look that works.™

P.O. Box 410, 525 Western Road, Schofield, WI 54476-0410 USA  
715.841.8757 • fax 715.841.8773 • [www.airolite.com](http://www.airolite.com)



Workmanship. Partnership. Leadership.

Printed in USA  
Copyright © 2020 The Aiolite Company, LLC  
Aiolite Finishes 02.ARL1009 R6 4-2020 SP